






## Special advantages:

-  For operating temperatures of -40°C (-40°F) to +35°C (+95°F).
-  For temperatures of -40°C (-40°F) to +50°C (+122°F).
-  High plasticity and flexibility.
-  Electrically insulating and diffusion resistant.
-  Ideally suitable for complex surfaces of pipeline components.

## Plastic petrolatum tape for sealing and for corrosion prevention at metallic components, pipes and armatures with operating temperatures up to +35°C (+95°F).

For a century now, DENSO Group Germany has been representing experience, quality and reliability for corrosion prevention and sealing technology. The success of the internationally leading corporation is based on the development of the "DENSO-Tape", which was already patented in 1927 as the first product worldwide for the passive corrosion prevention of pipelines. Since then, the DENSO Group Germany has been establishing and guaranteeing the highest quality standards with technically trend-setting products. Research, development and production take place exclusively in Germany. Our employees continuously implement safe and individual solutions in a personal cooperation with the customer.

## Description

**DENSO<sup>®</sup>-Tec** is a corrosion prevention tape that can be processed cold on the basis of petrolatum.

DENSO<sup>®</sup>-Tec consist of an impregnated polypropylene carrier nonwoven, which is coated on both sides with a corrosion prevention petrolatum mastic. The petrolatum mastic is stabilized by polymer additives, which means that it can be used at operating temperatures of -40°C (-40 °F) to +35°C (+95°F).

DENSO<sup>®</sup>-Tec is impermeable for water and highly resistant against hydrous electrolyte solution.

DENSO<sup>®</sup>-Tec is based on more than 90 years of experience of the DENSO Group Germany in the production of

high quality corrosion prevention products on petrolatum basis.

DENSO<sup>®</sup>-Tec is used in many applications, e.g. as

- Corrosion prevention for structural metallic components in buildings and above ground systems,
- Corrosion prevention of metal parts or pipe systems inserted into concrete or screed,
- Galvanic separation layer for metallic constructions,
- Corrosion prevention of cooling lines or heat insulating insulations.

DENSO<sup>®</sup>-Tec will be wrapped as insulation layer at least with one layer and, as corrosion prevention encasement with

50% overlap, at least with two layers, or processed layer by layer with an adequate overlap.

An alternative corrosion prevention tape with a laminated PP film is available with **DENSO<sup>®</sup>-Plast** for buried pipelines, which provides an increased resistance against washing out, e.g. due to rising and falling groundwater.

**DENSO<sup>®</sup>-Tape MT** (+60°C, +140°F), **DENSO<sup>®</sup>-Feu** (+70°C, +158°F) and **DENSO<sup>®</sup>-Cal** (+110°C, +230°F) are additional corrosion prevention tapes with the proven DENSO quality for applications with higher temperature requirements.

## Typical product properties

Property	Unit	Typical value	Required value	Test method
Thickness	mm	app. 1.1	-	-
Carrier	-	Polypropylene nonwoven	-	-
Specific electrical insulation resistance	$\Omega \text{ m}^2$	$\geq 10^7$	$\geq 10^6$	EN 12068
Drip resistance 48h, +50°C (+122°F)	-	No dripping	No dripping	EN 12068
Dripping point	°C (°F)	app. +60 (+140)	-	
Low temperature unrolling test +5°C (+23°F)	-	passed	No separation, no crack development	EN 12068
Saponification value (petrolatum mastic)	mg (KOH) / g	$\leq 10$	<25	EN 12068
UV stability	-	good	-	-
Operating temperature	°C (°F)	-40 to +35 (-40 to +95)	-	-
For temperatures of	°C (°F)	-40 to +50 (-40 to +122)	-	-

## Ordering information and packaging

Roll length 10 m

Width [mm]	Number of rolls per box	Tape length per box (m)	Tape surface per box (m <sup>2</sup> )	Weight per box app. [kg]
50	24	240	12	13,2
100	12	120	12	13,2
150	6	60	9	10,0
200	6	60	12	13,2

Additional dimensions available on request.

## Storage

When stored in its original, unopened packaging, **DENSO®-Tec** can be stored for at least 60 months after the manufacturing date.

Storage temperature:  $\leq +30^\circ\text{C}$  (+86°F)

The product must be stored dry, without load on the front surface.

### DENSO GmbH

P.O. Box 150120 | 51344 Leverkusen | Germany  
Phone: +49 214 2602-0  
[www.denso-group.com](http://www.denso-group.com) | [info@denso-group.com](mailto:info@denso-group.com)

Our product information, our application recommendations and other product related documents are made for your convenience only. Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith. All information contained in this document is to be used as a guide and does not constitute a warranty of specification. The information contained in the document is subject to change without notice. For this reason, no liability can be accepted for inaccurate advice or any failure to provide advice.

The user is responsible for checking the applications of the product and verifying its suitability for the intended use. Our General Terms of Sale, which are available at [www.denso-group.com](http://www.denso-group.com), shall be decisive without any exception.

This is a translation from the original German product information. In case of any discrepancy or any dispute arising on the interpretation of this product information, the German text of the respective German product information, which is available at [www.denso-group.com](http://www.denso-group.com), shall be decisive. The legal relationship shall be governed by German law.